

Epoxy Hardeners

| Sr. No. | Products | Solids (% NVM) | Colour (Gardner) | Viscosity @ 25 °C (cPs) | Epoxy equivalent weight | Hydroxyl Value (mg KOH/g) | PHR with epoxy resin (EEW=190) | Thin film set time (200 μ WFT) 25 °C | Key Properties | Marine Coating | Pro- tective Coating | Industrial Coatings | Construc- tion Con- crete |
|---------|----------|----------------|------------------|-------------------------|-------------------------|---------------------------|--------------------------------|--------------------------------------|----------------|----------------|----------------------------|---------------------|---------------------------------|
|---------|----------|----------------|------------------|-------------------------|-------------------------|---------------------------|--------------------------------|--------------------------------------|----------------|----------------|----------------------------|---------------------|---------------------------------|

EPOXY DILUENTS

| | | | | | | | | | | | | | |
|---|---------|--------------|----|---------|-----------|-----------|--------|--|---|---|---|---|---|
| 1 | AP 8016 | Solvent free | 10 | 40 - 55 | 425 - 525 | NA | 2 - 20 | | Reactive diluent as a viscosity reducer and flexibilizer. | ✓ | ✓ | ✓ | ✓ |
| 2 | AP 8030 | Solvent free | 10 | 70 - 90 | NA | 160 - 200 | 2 - 20 | | Non reactive resin modifier | ✓ | ✓ | ✓ | ✓ |