

# Epoxy Hardeners

Sr. No.	Products	Solids (% NVM)	Colour (Gardner)	Viscosity @ 25 °C (cPs)	Amine Value (mg KOH/g)	AHEW	PHR with epoxy resin (EEW=190)	Thin film set time (200 μ WFT) 25 °C	Key Properties	Pro- tective Coating	Crack injection & grouts	Adhesive, sealants and putties	Concrete primer
<b>LOW VISCOSITY PHENALKAMIDE</b>													
1	AP 2559	Solvent free	12	500 - 1200	335 - 385	95	50	8	Low viscosity, rapid cure with good flexibility and better adhesion to concrete surface.	✓	✓	✓	✓
2	AP 2560	Solvent free	12	400 - 700	350 - 400	95	50	10	Low viscosity, rapid cure at ambient and low temperature with high mechanical and better adhesion to concrete surface.	✓	✓	✓	✓